

## Low-frequency optics on $\text{Sr}_{(1-x)}\text{Ca}_x\text{RuO}_3$

*Monday, 23 July 2012 20:00 (2 hours)*

Marc Scheffler, 1. Physikalisches Institut, Universität Stuttgart, 70550 Stuttgart, Germany

Diana Geiger, 1. Physikalisches Institut, Universität Stuttgart, 70550 Stuttgart, Germany

Martin Dressel, 1. Physikalisches Institut, Universität Stuttgart, 70550 Stuttgart, Germany

Melanie Schneider, I. Physikalisches Institut, Georg-August-Universität Göttingen, 37077 Göttingen, Germany

Philipp Gegenwart, I. Physikalisches Institut, Georg-August-Universität Göttingen, 37077 Göttingen, Germany

The pseudo-cubic perovskite ruthenates  $\text{SrRuO}_3$  and  $\text{CaRuO}_3$  have recently attracted interest due to their unconventional electronic properties. For both materials, non-Fermi liquid behavior has been reported in previous optical studies at infrared frequencies. In addition to these two pure compounds, the doping series  $\text{Sr}_{(1-x)}\text{Ca}_x\text{RuO}_3$  offers a rich phase diagram: going from the itinerant ferromagnet  $\text{SrRuO}_3$  to the paramagnet  $\text{CaRuO}_3$ , there are indications for a quantum phase transition at  $x$  approximately 0.8.

Using low-frequency optical spectroscopy, we have studied  $\text{Sr}_{(1-x)}\text{Ca}_x\text{RuO}_3$  thin-film samples of very high quality, which were prepared by metalorganic aerosol deposition. In order to be sensitive to the small energy scales expected close to the quantum phase transition, we address the THz and GHz frequency ranges at temperatures down to 2 K. We present optical data, in particular the frequency-dependent conductivity, and discuss it in the framework of the extended Drude model with frequency-dependent relaxation rates and effective masses. While for pure  $\text{SrRuO}_3$  as well as for doped systems (approaching the quantum phase transition) we find conventional metallic Drude behavior at frequencies below 1 THz,  $\text{CaRuO}_3$  exhibits highly unusual optical properties: the relaxation rate increases strongly with frequency. We compare the optical data to dc measurements and discuss them with respect to the temperature ranges with non-Fermi liquid behavior.

**Primary author:** SCHEFFLER, Marc (Universität Stuttgart, Germany)

**Presenter:** SCHEFFLER, Marc (Universität Stuttgart, Germany)

**Session Classification:** Poster Session 1

**Track Classification:** Transition Metal Oxides